

BOOKBINDING HOT MELT

SW6092

Application: For the spine bonding of magazines, catalogues, albums, printshop works and for all standard art paper qualities, up to 200gram.

Characteristics: Excellent flexibility & bonding, with clear melting and an odor-free formula.

Specification:

Polymer basis	Ethylene vinyl acetate
Viscosity at 160 °c (mPa s)	6,000 - 8,000
Softening point	90 - 100 °c
Supply form	Clear transparent in granule
Application temperature	150 - 180 °c

Packaging & Storage: in 25 kg kraft bag. 40 bags/ pallet
Shelf life of 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.