

LAMINATION PUR (POLYURETHANE)**PUR8667**

Application: For lamination of PVC, PET, paper, aluminum film, on melamine board, multi-layer board, crust board, carbon board, etc.

Characteristics: Provides strong initial and final adhesion, compatible with a variety of materials in various environments, with excellent surface finish.

Specification:

Polymer basis	Polyurethane
Viscosity at 130°C (mPa s)	7,000 - 9,000
Coating weight	20-60 g/m ²
Open time /25°C	3 ~ 10 mins
Complete curing time	24 ~72 hours
Temperature resistance	-40 - 120°C
Application temperature	130 - 150°C

Packaging & Storage: in a 20/ 200 kg net steel drum package.
Shelf life of 12 months, in original package, cool and dry.

TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

FREE BIRD 
Adhesives