

REACTIVE PUR EDGE BANDING

PUR6818

Application: 100% single-component moisture-cured polyurethane hot melts, designed for automatic edgebanders with PUR applicator.

Characteristics: Processing from moisture-proof sealed drums, our Reactive Polyurethane (PUR) offers good initial and ultimate adhesion with moderate open time, makes it suitable for different environments.

Specification:

Polymer basis	Polyurethane
Viscosity at 130°C (mPa s)	40,000 - 60,000
Complete curing time	48 hours
Supply form	Natural white solid form
Application temperature	130 - 160°C

Packaging & Storage: in a 20 kg steel drum package. 24 drums/ pallet
Shelf life of 12 months, in original package, cool and dry.

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

FREE BIRD ®
Adhesives