

REACTIVE PUR BOOKBINDING**PUR6318**

Application: 100% solid single-component reactive hot melt adhesive, suitable for adhesive backing in the bookbinding industry, with high initial strength for materials such as paper, PET, PVC, and thin metal sheets.

Features: Stable viscosity when heated, with a flexible adhesive layer. High peel strength after curing, excellent heat and moisture resistance, and strong chemical durability.

Specification:

Polymer basis	Polyurethane
Viscosity at 120°C (mPa s)	60,000
Open time	30 seconds
Complete curing time	2-4 hours
Supply form	White to slightly yellow solid form
Application temperature	110 - 140°C

Packaging & Storage: 2kg/bag, 20kg/drum, 200kg/drum.

Shelf life of 6 months, in original package, cool and dry.

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

**TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT**

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

FREE BIRD 
Adhesives