

**EDGE BANDING HOT MELT****SW8062**

**Application:** Unfilled. Engineered for stable and continuous manual operation, for straight and contour edge-banding, with low process temperature, from 130°C/ 266°F.

**Characteristics:** Provides excellent adhesion and high bond yield, with a clear melt and reliable thermal stability. (Comparable to Jowat 282.40)

**Specification:**

|                               |                                |
|-------------------------------|--------------------------------|
| Polymer basis                 | Ethylene-Vinyl Acetate         |
| Viscosity<br>at 150°C (mPa s) | 20,000 - 30,000                |
| Softening point               | 85 - 95°C                      |
| Supply form                   | Transparent yellow<br>granules |
| Application temperature       | 130 - 150°C                    |

**Packaging & Storage:** in a 25 kg kraft bag. 40 bags/ pallet  
Shelf life of 24 months, in original package, cool and dry.

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC  
CHEMICAL PLANT

E-mail: [sales@swadhesive.com](mailto:sales@swadhesive.com)

[www.swhotmeltglue.com](http://www.swhotmeltglue.com)

**FREE BIRD**   
Adhesives