EDGE BANDING HOT MELT

SW826L

Application: Standard value option for high-speed automatic machines, suitable for a variety of edgebands (i.e. PVC, ABS, paper, and veneer).

Characteristics: Excellent cost performance, provides strong adhesion, high bond yield, and oxidation stability.

Specification:

Polymer basis	Ethylene-Vlnyl Acetate
Viscosity at 200 °c (mPa s)	50,000 - 60,000
Softening point	90 - 100 °c
Supply form	Opaque white granules
Application temperature	180 - 210 °c

Packaging & Storage: in a 25 kg kraft bag. 40 bags/ pallet Shelf life of 24 months, in original package, cool and dry.

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC CHEMICAL PLANT

 $\hbox{E-mail: sales@swadhesive.com}$

www.swhotmeltglue.com

