

EDGE BANDING HOT MELT

SW828J

Application: Engineered for stable and continuous manual operation, for straight and contour edge-banding, with low process temperature, from 130°C/ 266°F.

Characteristics: Provides excellent adhesion and high bond yield with reliable thermal stability. (Comparable to Jowat 282.20)

Specification:

Polymer basis	Ethylene-VInyl Acetate
Viscosity at 160°C (mPa s)	20,000 - 30,000
Softening point	85 - 90°C
Supply form	Natural white granules
Application temperature	130 - 150°C

Packaging & Storage: in a 25 kg kraft bag. 40 bags/ pallet
Shelf life of 24 months, in original package, cool and dry.

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

