

PACKAGING HOT MELT

SW5020

Application: For bonding purposes in packaging processes, e.g. for uncoated cartons, trays, and folding boxes.

Characteristics: Very good bonding capabilities with good thermal stability and temperature resistance, ideal for automated packaging lines.

Specification:

Polymer basis	Ethylene-Vinyl Acetate
Viscosity at 160 °c (mPa s)	3,000 - 4,000
Softening point	110 - 115 °c
Supply form	Yellow, translucent melt in granules
Application temperature	150 - 170 °c

Packaging & Storage: in 25 kg kraft bag. 40 bags/ pallet
Shelf life of 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.