

EDGE BANDING HOT MELT**SW818S**

Application: Cost-effective option for automatic machines, suitable for a variety of edgebands including PVC, ABS, paper, and veneer.

Characteristics: Competitive pricing, excellent adhesion, and machinability, suitable for a wide range of machine feed speeds.

Specification:

Polymer basis	Ethylene-Vinyl Acetate
Viscosity at 200 °c (mPa s)	50,000 - 60,000
Softening point	90 - 100 °c
Supply form	Opaque white in granule
Application temperature	180 - 210 °c

General guidance: For best bonding results, the materials to be used must be free of dust, oil, and grease, and be dry.

Packaging: 25 kg net weight, in non-woven bag

Storage: 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC

CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

FREE BIRD 
Adhesives