

PACKAGING HOT MELT**SW5060**

Application: For bonding purposes in packaging processes, especially for glossy, varnished, laminated paper packaging, e.g. cartons, trays, and folding boxes.

Characteristics: Very good adhesion, high heat resistance of the bond, resistance to oxidation, minimal odor and smoke.

Specification:

Polymer basis	Polyolefin
Viscosity at 160 °c (mPa s)	3,000 - 4,000
Softening point	110 - 115 °c
Supply form	White, translucent melt in granules
Application temperature	150 - 170 °c

Packaging & Storage: in 25 kg kraft bag. 40 bags/ pallet
Shelf life of 24 months, in original package, cool and dry (15-35°C).

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.