## **EDGE BANDING HOT MELT**

## **SW858A**

**Application:** Primary option for manual and slow automatic machines, straight and contour edge-banding, with low process temperature.

Characteristics: Provides excellent adhesion and high bond yield with good machinability and color stability.

## **Specification:**

Polymer basis	Ethylene-Vlnyl Acetate
Viscosity at 180 °c (mPa s)	30,000 - 40,000
Softening point	80 - 90 °c
Supply form	Natural white granules
Application temperature	140 - 170 °c

**Packaging & Storage:** in a 25 kg kraft bag. 40 bags/ pallet Shelf life of 24 months, in original package, cool and dry.

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

