

**REACTIVE PUR EDGE BANDING****PUR6818**

**Application:** 100% single-component moisture-cured polyurethane hot melts, designed for automatic edgebanders with PUR applicator.

**Characteristics:** Processing from moisture-proof sealed drums, our Reactive Polyurethane (PUR) offers good initial and ultimate adhesion with moderate open time, makes it suitable for different environments.

**Specification:**

Polymer basis	Polyurethane
Viscosity at 130°C (mPa s)	40,000 - 60,000
Complete curing time	48 hours
Supply form	Natural white solid form
Application temperature	120 - 150°C

**Packaging & Storage:** in a 20 kg steel drum package. 24 drums/ pallet  
Shelf life of 12 months, in original package, cool and dry.

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

**TIANJIN SHENG-WANG ELECTRONIC  
CHEMICAL PLANT**

**E-mail:** [sales@swadhesive.com](mailto:sales@swadhesive.com)

**[www.swhotmeltglue.com](http://www.swhotmeltglue.com)**

**FREE BIRD**   
Adhesives