## **EDGE BANDING HOT MELT**

SW816A

**Application:** Premium option for high-speed automatic machines, suitable for a variety of edgebands (i.e. PVC, ABS, paper, and veneer).

**Characteristics:** Provides excellent bonding capabilities, very high bond yield, with virtually invisible bondline. (Reference to Jowat 288.70)

## **Specification:**

| Polymer basis                  | Ethylene-Vlnyl Acetate   |
|--------------------------------|--------------------------|
| Viscosity<br>at 200 °c (mPa s) | 50,000 - 60,000          |
| Softening point                | 90 - 100 °c              |
| Supply form                    | Opaque white<br>granules |
| Application temperature        | 180 - 210 °c             |

**Packaging & Storage:** in a 25 kg kraft bag. 40 bags/ pallet Shelf life of 24 months, in original package, cool and dry.

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC CHEMICAL PLANT

 $\hbox{E-mail: sales@swadhesive.com}$ 

www.swhotmeltglue.com

