

REACTIVE PUR PROFILE WRAPPING**PUR6632**

Application: 100% single-component moisture-cured polyurethane hot melts, designed for wrapping wood, metal, plastic profiles with PVC, CPL, veneer, decor paper, etc.

Characteristics: Processing from moisture-proof sealed drums, our Reactive Polyurethane (PUR) offers good initial and ultimate adhesion with excellent resistance to heat and solvent, suitable for different environments.

Specification:

Polymer basis	Polyurethane
Viscosity at 130°C (mPa s)	30,000 - 40,000
Specific gravity (g/cm ³)	approx. 1.05
Open time /25°C	20-40 sec
Initial strength (10min, PVC/ Aluminum, 180°C)	1.6 N/mm
Final strength (3 days, PVC/ Aluminum, 180°C)	> 2.0 N/mm
Application temperature	110 - 140 °C

Packaging & Storage: in a 20kg/ 190kg net metal drum.
Shelf life of 12 months, in original package, cool and dry.

**TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT**

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

FREE BIRD 
Adhesives