EDGE BANDING HOT MELT

SW8062A

Application: Unfilled. Featured option for manual machines, straight and contour edge-banding, with low process temperature.

Characteristics: Provides excellent adhesion and high bond yield with clear melting and good color stability.

Specification:

Polymer basis	Ethylene-VInyl Acetate
Viscosity at 150°c (mPa s)	20,000 - 30,000
Softening point	85 - 95 °c
Supply form	Transparent yellow granules
Application temperature	120 - 150 °c

Packaging & Storage: in a 25 kg kraft bag. 40 bags/ pallet Shelf life of 24 months, in original package, cool and dry.

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC CHEMICAL PLANT

 $\hbox{E-mail: sales@swadhesive.com}$

www.swhotmeltglue.com

