

REACTIVE PUR EDGE BANDING**PUR6818**

Application: 100% single-component moisture-cured polyurethane hot melts, designed for automatic edgebanders with PUR applicator.

Characteristics: Processing from moisture-proof sealed drums, our Reactive Polyurethane (PUR) offers good initial and ultimate adhesion with moderate open time, makes it suitable for different environments.

Specification:

Polymer basis	Polyurethane
Viscosity at 150°C (mPa s)	65,000 - 75,000
Complete curing time	48 hours
Supply form	Natural white solid form
Application temperature	130 - 150°C

Packaging & Storage: in 20 kg steel drums (24 drums per pallet), as well as 400 g and 2 kg slots. Shelf life of 12 months, in original package.

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

FREE BIRD 
Adhesives