

EDGE BANDING HOT MELT

SW858L

Application: Standard value option for medium-to-slow speed automatic machines, suitable for a variety of edgebands (i.e. PVC, ABS, paper, and veneer).

Characteristics: Excellent cost performance, provides strong adhesion, high bond yield, and oxidation stability.

Specification:

Polymer basis	Ethylene-Vinyl Acetate
Viscosity at 180 °c (mPa s)	40,000 - 50,000
Softening point	85 - 95 °c
Supply form	Opaque white granules
Application temperature	150 - 180 °c

Packaging & Storage: in a 25 kg kraft bag. 40 bags/ pallet
Shelf life of 24 months, in original package, cool and dry

Remarks: All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC
CHEMICAL PLANT

E-mail: sales@swadhesive.com

www.swhotmeltglue.com

