

**EDGE BANDING HOT MELT**

**SW828J**

**Application:** Primary option for manual machines, straight and contour edge-banding, with low process temperature, from 130°C/ 266°F.

**Characteristics:** Provides excellent adhesion and high bond yield with good machinability and color stability.

**Specification:**

Polymer basis	Ethylene-VInyl Acetate
Viscosity at 160 °c (mPa s)	20,000 - 30,000
Softening point	85 - 90°C
Supply form	Natural white granules
Application temperature	130 - 150 °c

**Packaging & Storage:** in a 25 kg kraft bag. 40 bags/ pallet  
Shelf life of 24 months, in original package, cool and dry.

**Remarks:** All data indicated are characteristics represented as average values. Our technical data sheets are revised to represent the latest information. This edition is valid on the date of compilation.

TIANJIN SHENG-WANG ELECTRONIC  
CHEMICAL PLANT

E-mail: [sales@swadhesive.com](mailto:sales@swadhesive.com)

[www.swhotmeltglue.com](http://www.swhotmeltglue.com)

